



AEROSPACE MATERIAL SPECIFICATION

AMS1630™**REV. D**

Issued 1978-01
Revised 2018-11
Reaffirmed 2024-11

Superseding AMS1630C

(R) Cleaner, Carpet
Shampoo Type

RATIONALE

CSMA test specifications are no longer available requiring modification to the specification. Requirement for a safety data sheet added. Additional details are required in order for the washability and color fastness testing to be performed. Clarification of the cleaning required for the flame retardancy test added.

AMS1630D has been reaffirmed to comply with the SAE Five-Year Review policy.

1. SCOPE

1.1 Form

This specification covers a shampoo type carpet cleaner in the form of a liquid.

1.2 Application

This cleaner has been used typically with shampooing machines for in-place cleaning of aircraft carpets, but usage is not limited to such applications.

1.3 Safety - Hazardous Materials

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2024 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, or used for text and data mining, AI training, or similar technologies, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS1630D/>

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS4037	Aluminum Alloy, Sheet and Plate, 4.4Cu - 1.5Mg - 0.60Mn (2024, -T3 Sheet/-T351 Plate with 1-1/2% Alcad), Solution Heat Treated
AMS4041	Aluminum Alloy, Sheet and Plate, Alcad, 4.4Cu - 1.5Mg - 0.60Mn (2024, -T3 Sheet/-T351 Plate with 1-1/2% Alcad), Solution Heat Treated, Cold Worked and Naturally Aged
AMS4045	Aluminum Alloy Sheet and Plate, 5.6Zn - 2.5Mg - 1.6Cu - 0.23Cr 7075: (-T6 Sheet, -T651 Plate), Solution and Precipitation Heat Treated
AMS4049	Aluminum Alloy, Sheet and Plate, Alcad, 5.6Zn - 2.5Mg - 1.6Cu - 0.23Cr (Alcad 7075; -T6 Sheet - T651 Plate), Solution and Precipitation Heat Treated
AMS-P-83310	Plastic Sheet, Polycarbonate, Transparent
ARP1917	Clarification of Terms Used in Aerospace Metals Specifications

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM D56	Flash Point by Tag Closed Tester
ASTM D1193	Reagent Water
ASTM D1335	Tuft Bind of Pile Floor Coverings
ASTM F483	Total Immersion Corrosion Test for Aircraft Maintenance Chemicals
ASTM F484	Stress Cracking of Acrylic Plastics in Contact with Liquid or Semi-Liquid Compounds
ASTM F502	Effects of Cleaning and Chemical Maintenance Materials on Painted Aircraft Surfaces
ASTM F1104	Preparing Aircraft Cleaning Compounds, Liquid Type, Water Base, for Storage Stability Testing
ASTM F1110	Sandwich Corrosion Test

2.3 U.S. Government Publications

Copies of these documents are available online at <http://quicksearch.dla.mil>.

MIL-PRF-25690	Plastic Sheets and Parts, Modified Acrylic Base, Monolithic, Crack Propagation Resistant
---------------	--

2.4 Federal Aviation Administration Regulations

Available from Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402. This can also be viewed online at www.faa.gov.

FAR Part 25	Airworthiness Standards; Transport Category Airplanes
-------------	---

2.5 AATCC Publications

Available from American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, NC 27709-2215.

AATCC Test Method 138 Cleaning: Washing of Textile Floor Coverings

2.6 Other Publications

ANSI Z400.1/Z129.1 Hazardous Workplace Chemicals - Hazard Evaluation and Safety Data Sheet and Precautionary Labeling Preparation

3. TECHNICAL REQUIREMENTS

3.1 Composition

The composition of the cleaner shall be optional with the manufacturer but shall yield a product conforming to the requirements of 3.2.

3.2 Properties

Cleaner shall conform to the following requirements; tests shall be performed in accordance with specified test methods on the product supplied in concentrated form and, when specified, at use dilution recommended by the manufacturer using ASTM D1193, Type IV, water for dilution.

3.2.1 Solubility

Cleaner shall be readily miscible with both hard and soft water and shall produce no detectable precipitate, determined in accordance with 3.2.1.1.

3.2.1.1 Prepare a solution of 1 mL of cleaner in 99 mL of ASTM D1193, Type IV, water in a 100 mL glass-stoppered, graduated cylinder. Prepare a second sample of 1 mL of cleaner in 99 mL of synthetic tap water made up as in 3.2.1.1.1. Allow the two samples to stand undisturbed for not less than one hour and examine for evidence of scum or sediment.

3.2.1.1.1 Prepare a solution of synthetic tap water as shown in Table 1.

Table 1 - Synthetic tap water

Ingredient	Amount
AR Calcium Acetate, $\text{Ca}(\text{C}_2\text{H}_3\text{O}_2)_2 \cdot 2\text{H}_2\text{O}$	0.20 gram $\pm$ 0.005 gram
AR Magnesium Sulfate, $\text{MgSO}_4 \cdot 7\text{H}_2\text{O}$	0.15 gram $\pm$ 0.005 gram
AR Sodium Chloride, NaCl	0.12 gram $\pm$ 0.005 gram
ASTM D1193, Type III, Water	To make 1 liter

3.2.1.1.1.1 The pH of the reagent water shall be 6.5 to 7.5. The pH of the synthetic tap water solution shall be approximately 6.8 and within the range 6.5 to 7.5.

3.2.2 Flash Point

Shall be not lower than 60 °C (140 °F), determined in accordance with ASTM D56.

3.2.3 Corrosion of Metal Surfaces

3.2.3.1 Sandwich Corrosion

Specimens of AMS4045 and AMS4049 aluminum alloy, after testing in accordance with ASTM F1110 on cleaner both in the concentrated form and at use dilution, shall not show corrosion worse than control panels tested with ASTM D1193, Type IV, water.

3.2.3.2 Total Immersion Corrosion

Cleaner, both in the concentrated form and at use dilution, shall neither produce evidence of staining, pitting, or discoloration of the panels nor cause a weight change of any panel greater than 0.3 mg/cm² per 24 hours, determined in accordance with ASTM F483 on panels of AMS4037, AMS4045, and either AMS4041 or AMS4049 aluminum alloys.

3.2.4 Effect on Transparent Plastics

3.2.4.1 Cleaner, both in the concentrated form and at use dilution, shall not craze, stain, or discolor MIL-PRF-25690, Type C, acrylic plastic, determined in accordance with ASTM F484.

3.2.4.2 The cleaner shall not craze, stain, or discolor AMS-P-83310 polycarbonate plastics, determined in accordance with test procedures specified in ASTM F484 on specimens stressed for 10 minutes $\pm$ 1 minute to an outer fiber stress of 2000 psi (13.0 MPa).

3.2.5 Effect on Painted Interior Surfaces

Cleaner, at use dilution, shall neither decrease the hardness of the paint film by more than two pencil hardness levels nor shall it produce streaking, discoloration, or other damage to the paint film, determined in accordance with ASTM F502.

3.2.6 Effect on Carpeting

Manufacturer and specification details of the test carpet shall be determined by the purchaser, and if not determined by the purchaser, shall be specified by the supplier and the carpet specifications shall be included in the report.

3.2.6.1 Discoloration

Cleaner, at use dilution, shall neither cause discoloration or other adverse effects on carpeting nor shall it show a force loss greater than 1 pound force (4.5 N), determined in accordance with 3.2.6.1.1.

3.2.6.1.1 Cut two adjacent pieces, approximately 6 x 12 inches (152 x 304 mm), from a section of test carpeting. One piece shall be used as a control sample; the other piece shall be sprayed uniformly with 25 to 50 mL of the cleaner at use dilution, allowed to dry for 24 hours $\pm$ 1 hour, and examined for discoloration, swelling of the latex backing, and other deleterious effects by comparing it with the control sample. Using a 50 pounds force (225 N) Dial PushPull Gauge and procedures in accordance with ASTM D1335, pull an individual loop of pile through the top of the carpeting and record the pounds force required. Take four readings on the test sample and four on the control sample and average each set of readings. The difference in the average readings shall be less than one pound force (4.5 N).

3.2.6.2 Washability and Color Fastness

3.2.6.2.1 Two samples of test carpet shall be prepared according to AATCC Test Method 138. One test carpet sample shall have as the cleaning agent reagent water to ASTM D-1193, Ty IV and cleaned according to the steps outlined in AATCC Test Method 138. The other carpet sample shall have as the cleaning agent the test solution diluted to the at use dilution and the carpet is cleaned according to AATCC Test Method 138. The two samples are compared for color. Any color difference between the two carpet samples will be noted.

3.2.6.3 Flame Retardancy

Ten washings of the carpet with the cleaner at use dilution, cleaned according to the AATCC Test Method 138, shall not alter the burn rate characteristics of carpeting, determined in accordance with FAR 25.853.

3.2.7 Storage Stability

Cleaner, exposed to heat and cold in accordance with ASTM F1104, shall show no precipitation, stratification, layering, or separation.

3.3 Quality

The cleaner, as received by purchaser, shall be homogeneous, uniform in color, and free from skins and lumps and from foreign materials detrimental to usage of the cleaner.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of cleaner shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the cleaner conforms to the requirements of this specification.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Total immersion corrosion (3.2.3.2), effect on plastics (3.2.4), and effect on carpeting (3.2.6) are acceptance tests and shall be performed on each lot.

4.2.2 Preproduction Tests

All technical requirements are preproduction tests and shall be performed prior to or on the initial shipment of the cleaner to a purchaser, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.3 Sampling and Testing

Sufficient product shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three; a lot shall be all cleaner produced in a single production run from the same batches of raw materials under the same fixed conditions and presented for vendor's inspection at one time.

4.3.1 When a statistical sampling plan has been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3 and the report of 4.5 shall state that such plan was used.

4.4 Approval

4.4.1 Sample cleaner shall be approved by purchaser before cleaner for production use is supplied, unless such approval be waived by purchaser. Results of tests on production cleaner shall be essentially equivalent to those on the approved sample.

4.4.2 Vendor shall use ingredients, manufacturing procedures, and methods of inspection on production cleaner which are essentially the same as those used on the approved sample cleaner. If necessary to make any change in ingredients or manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in ingredients and/or processing and, when requested, sample cleaner. Production cleaner made by the revised procedure shall not be shipped prior to receipt of reapproval.