

AEROSPACE MATERIAL SPECIFICATION

Issued	1940-10
Revised	1991-04
Noncurrent	2004-03
Reaf Nonc	2011-04
Superseding AMS 2503E	

Black Finishing
Low Baking Enamel

NONCURRENT NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of March, 2004. It is recommended, therefore, that this specification not be specified for new designs.

"NONCURRENT" refers to those specifications that have been widely used and may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these specifications for future use in new designs. "NONCURRENT" specifications are available from SAE upon request.

This process specification covers the application of AMS 3110 primer and AMS 3120 alkyd enamel, both of which are noncurrent.

SAENORM.COM : Click to view the full PDF of AMS2503F

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2011 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS2503F>**

1. SCOPE:

1.1 Form:

This specification covers the engineering requirements for finishing aircraft parts and assemblies with a black enamel.

1.2 Application:

Primarily for parts and assemblies operating in service up to 350 °F (177 °C).

1.3 Safety - Hazardous Materials:

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or www.sae.org.

AMS 2400	Cadmium Plating
AMS 2470	Anodic Treatment of Aluminum Alloys, Chromic Acid Process
AMS 2471	Anodic Treatment of Aluminum Alloys, Sulfuric Acid Process, Undyed Coating
AMS 2475	Protective Treatments, Magnesium Alloys
AMS 2480	Phosphate Treatment, Paint Base
AMS 3110	Primer, Zinc Chromate
AMS 3120	Enamel, Glyceryl Phthalate, Black Baking

3. TECHNICAL REQUIREMENTS:

3.1 Preparation:

Parts, before being painted, shall be prepared as follows; elapsed time between preparatory treatments and priming shall be as short as practicable:

3.1.1 Aluminum and Aluminum Alloys: Both wrought and cast parts shall be anodized in accordance with AMS 2470 or AMS 2471.

3.1.1.1 Aluminum Assemblies: Aluminum alloy parts which are subsequently assembled with parts made of other materials constitute assemblies, shall be anodized in accordance with AMS 2470 or AMS 2471 prior to assembly, unless such other materials are masked. Anodizing shall be performed in accordance with AMS 2470 on aluminum assemblies where solutions could become entrapped.

3.1.2 Magnesium Alloys: Both wrought and cast parts shall be treated in accordance with AMS 2475. Machining of external surfaces shall be completed prior to such treatment.

3.1.3 Steel: Cadmium plated parts shall be thoroughly neutralized in accordance with AMS 2400. Unplated parts shall be cleaned free from oil, grease, dirt, and rust and then phosphate treated in accordance with AMS 2480.

3.2 Procedure:

3.2.1 Priming: One coat of AMS 3110 zinc chromate primer shall be applied to all surfaces of metallic parts requiring enameling, except as follows:

3.2.1.1 Anodized rivets shall not be primed as details.

3.2.1.2 Two coats of primer shall be applied to magnesium alloy parts.

3.2.2 Cleaning: When there are intervening operations between priming and enameling, such as assembling or additional machining, the parts shall be thoroughly cleaned by spraying with clean naphtha, or other solvent of low volatility, and given another coat of AMS 3110 zinc chromate primer before the first coat of enamel is applied.

3.2.3 Baking: Each coat of primer shall be baked at 250 to 300 °F (121 to 149°C) unless baking at a lower temperature or air drying is permitted by purchaser.

3.2.4 Enameling: The following requirements apply to all metallic surfaces which are exposed after parts are assembled in the power plant or aircraft. Magnesium alloy parts used as covers but not in contact with oil shall be enameled on both inside and outside surfaces except on contacting machined surfaces. Enameling of spot faces is optional.

3.2.4.1 Three coats of AMS 3120 black enamel shall be applied to magnesium alloy parts for use on other than aircraft power plants.

- 3.2.4.2 Two coats of AMS 3120 black enamel shall be applied to magnesium alloy parts for use on aircraft power plants and to parts of all other metals for all applications.
- 3.2.4.3 Each coat of enamel shall be thoroughly baked at not higher than 300 °F (149 °C) or preliminary coats may be air-dried dust-free and the final coat baked firm and hard at not higher than 300 °F (149 °C).
- 3.2.4.4 Enameling is not required on nonmetallic materials and associated metal parts, on threaded sections, or on removable steel parts.

3.3 Quality:

Painted surfaces, as received by purchaser, shall be smooth, uniform in color and gloss, and free from pinholes, sags, runs, heavy edges, foreign materials, and other imperfections detrimental to usage of the coating.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The processing vendor shall supply all samples for vendor's tests and shall be responsible for the performance of all required inspections. Purchaser reserves the right to sample and to perform any confirmatory inspection deemed necessary to ensure that finishing conforms to specified requirements.

4.2 Classification of Inspections:

Inspection for quality (3.3) and for coverage in accordance with drawing requirements or other instructions are acceptance inspections and shall be performed to represent each lot.

4.3 Sampling and Testing:

Each part shall be examined.

4.4 Reports:

The vendor of painted parts shall furnish with each shipment a report stating that the parts have been processed and inspected in accordance with the requirements of this specification and that they conform. This report shall include the purchase order number, AMS 2503F, part number, and quantity.

5. PREPARATION FOR DELIVERY:

5.1 Packaging:

- 5.1.1 Painted parts shall be handled and packaged to ensure that the required physical characteristics and properties of the coating are preserved.