

AEROSPACE MATERIAL SPECIFICATION

SAE AMS5132

REV. K

Issued 1941-11
Revised 2007-07
Reaffirmed 2012-04

Superseding AMS5132J

Steel, Bars
0.90 - 1.03C

(Composition similar to UNS G10950)

RATIONALE

AMS5132K has been reaffirmed to comply with the SAE five-year review policy.

1. SCOPE

1.1 Form

This specification covers a high-carbon steel in the form of bars.

1.2 Application

These bars have been used typically for dowels and other parts requiring close tolerances, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS 2259
AMS 2370

Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steels, Wrought Products and Forging Stock

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS5132K>**

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org

ASTM A 370 Mechanical Testing of Steel Products
ASTM E 350 Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - COMPOSITION

Element	min	max
Carbon	0.90	1.03
Manganese	0.15	0.50
Silicon	0.15	0.35
Phosphorus	--	0.040
Sulfur	--	0.050

3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Condition

Spheroidized annealed and cold finished; round bars shall be ground or polished.

3.3 Properties

Bars shall conform to the following requirements:

3.3.1 Hardness

Shall be not greater than specified in Table 2, determined in accordance with ASTM A 370 (See 8.2).

TABLE 2 - HARDNESS

Nominal Diameter or Distance Between Parallel Sides Inches	Nominal Diameter or Distance Between Parallel Sides Millimeters	Hardness, Maximum
Up to 0.125, incl	Up to 3.18, incl	302 HB or 32 HRC
Over 0.125 to 0.250, incl	Over 3.18 to 6.35, incl	277 HB or 29 HRC
Over 0.250 to 0.500, incl	Over 6.35 to 12.70, incl	241 HB or 23 HRC
Over 0.500	Over 12.70	207 HB or 95 HRB

3.3.2 Decarburization

Bars shall be free from any decarburization, determined microscopically at a magnification not exceeding 100X, unless bars are ordered to tolerances greater than those specified in 3.5 in which case the permissible maximum depth of decarburization shall be as agreed upon by purchaser and vendor.

3.3.3 Microstructure

Shall consist of uniformly distributed spheroidized carbides free from carbide network. Standards for acceptance for lamellar pearlite may be agreed upon by purchaser and vendor.

3.4 Quality

Bars, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the bars.

3.5 Tolerances

Shall conform to the requirements of Table 3.

TABLE 3A - DIAMETER TOLERANCES, INCH/POUND UNITS

Nominal Diameter or Distance Between Parallel Sides Inches	Tolerance, Inch Plus and Minus
Up to 0.125, excl	0.0002
0.125 to 0.500, excl	0.00025
0.500 to 1.500, incl	0.0005

TABLE 3B - DIAMETER TOLERANCES, SI UNITS

Nominal Diameter or Distance Between Parallel Sides Millimeters	Tolerance, Millimeter Plus and Minus
Up to 3.18, excl	0.005
3.18 to 12.70, excl	0.0064
12.70 to 38.10, incl	0.013

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of bars shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the bars conform to specified requirements.

4.2 Classification of Tests

All technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing

Shall be in accordance with AMS 2370.

4.4 Reports

The vendor of bars shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for hardness of each lot. This report shall include the purchase order number, heat and lot numbers, AMS 5132K, size, and quantity.

4.5 Resampling and Retesting

Shall be in accordance with AMS 2370.