

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 5700A

Issued 3-14-40
Revised 10-1-51

STEEL, CORROSION AND HEAT RESISTANT
14Cr - 14Ni - 2.4W - 0.4Mo

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. FORM: Bars, forgings, and forging stock.
3. APPLICATION: Primarily for parts, such as exhaust valves and valve seat inserts, requiring resistance to corrosion by combustion products at operating temperatures.
4. COMPOSITION:

Check Analysis
Under Min or Over Max

Carbon	0.40 - 0.50	0.02	0.02
Manganese	0.70 max	--	0.03
Silicon	0.30 - 0.80	0.05	0.05
Phosphorus	0.030 max	--	0.005
Sulfur	0.030 max	--	0.005
Chromium	13.00 - 15.00	0.15	0.15
Nickel	13.00 - 15.00	0.15	0.15
Molybdenum	0.20 - 0.50	0.03	0.03
Tungsten	1.75 - 3.00	0.10	0.10

5. CONDITION:

- 5.1 Bars and Forgings: Annealed, in a machinable condition, having a uniform, refined structure. All hexagons, and other bars 2.75 in. and less in diameter or distance between parallel sides shall be cold finished.
- 5.2 Forging Stock: As ordered by the forging manufacturer.

6. TECHNICAL REQUIREMENTS:

- 6.1 Heat Treatment: Material shall be heated to 1650 F $\pm$ 25, held at that temperature for 1-2 hr and cooled in air.
- 6.2 Hardness: Shall be not higher than Brinell 285 or equivalent.
7. QUALITY: Material shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external defects detrimental to fabrication or to performance of parts.
8. TOLERANCES: Unless otherwise specified, tolerances shall conform to the latest issue of AMS 2241 as applicable. Diameter and thickness tolerances shall be as specified below:

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."