

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

Issued JAN 1957
Revised JUN 1996

Superseding AMS 5776C

STEEL, CORROSION AND HEAT RESISTANT, WELDING WIRE
12.5Cr (SAE 51410)

UNS S41001

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat resistant steel in the form of welding wire.

1.2 Application:

This wire has been used typically as filler metal for gas-metal-arc or gas-tungsten-arc welding of steels of similar composition requiring joints with strength and corrosion resistance comparable to those of the basis metal, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

- AMS 2248 Chemical Check Analysis Limits, Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
- AMS 2371 Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock
- AMS 2813 Packaging and Marking of Packages of Welding Wire, Standard Method
- AMS 2814 Packaging and Marking of Packages of Welding Wire, Premium Quality
- AMS 2816 Identification, Welding Wire, Tab Marking Method
- AMS 2819 Identification, Welding Wire, Direct Color Code System
- AMS 5504 Steel Sheet, Strip, and Plate, Corrosion and Heat Resistant, 12.5Cr (SAE 51410), Annealed

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

2.1 (Continued):

ARP1876 Weldability Test for Weld Filler Metal Wire
 ARP4926 Alloy Verification and Chemical Composition Inspection of Welding Wire

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM E 18 Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials
 ASTM E 353 Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Wire Composition:
(R)

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	0.10	0.15
Manganese	--	1.00
Silicon	--	1.00
Phosphorus	--	0.025
Sulfur	--	0.015
Phosphorus + Sulfur	--	0.030
Chromium	11.50	13.50
Nickel	--	0.75
Molybdenum	--	0.50
Aluminum	--	0.05
Copper	--	0.50
Tin	--	0.05
Nitrogen	--	0.08

3.1.1 Chemical analysis of initial ingot, bar, or rod stock before drawing is acceptable provided
 (R) processes used for drawing or rolling, annealing, and cleaning are controlled to ensure continued conformance to composition requirements.

3.1.2 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

3.2 Condition:

(R)

Cold worked, bright finish, in a temper and with a surface finish which will provide proper feeding of the wire in machine welding equipment.

3.3 Fabrication:

3.3.1 In-process annealing between cold rolling or drawing operations shall be performed in a

(R)

protective atmosphere to avoid surface oxidation and adsorption of other extraneous elements.

3.3.2 Butt welding is permissible provided both ends to be joined are alloy verified using a method or methods capable of distinguishing the alloy from all other alloys processed within the facility or the repair is made at the wire processing station. The butt weld shall not interfere with uniform, uninterrupted feeding of the wire in machine welding equipment.

(R)

3.3.3 Drawing compounds, oxides, dirt, oil, and other foreign materials shall be removed by cleaning processes which will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.

(R)

3.4 Properties:

Wire shall conform to the following requirements:

3.4.1 Weldability: Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds. ARP1876 may be used to resolve disputes.

(R)

3.4.2 Response to Heat Treatment: Weld metal deposits, approximately 1/4 inch (6.4 mm) in thickness, deposited on AMS 5504 steel shall attain hardness of 35 to 45 HRC, or equivalent (See 8.2), determined in accordance with ASTM E 18, after being heated to 1750 °F ± 10 (954 °C ± 6), held at heat for 30 minutes ± 3, and cooled in still air.

3.4.3 Spooled Wire: Shall conform to 3.4.3.1 and 3.4.3.2.

3.4.3.1 Cast: Wire, wound on standard 12-inch (305-mm) diameter spools, shall have imparted to it a curvature such that a specimen sufficient in length to form one loop with a 1-inch (25-mm) overlap, when cut from the spool and laid on a flat surface, shall form a circle 15 to 50 inches (381 to 1270 mm) in diameter.

(R)

3.4.3.2 Helix: The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 1 inch (25 mm).

3.5 Quality:

Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.6 Sizes and Tolerances:

Wire shall be supplied in the sizes and to the tolerances shown in 3.6.1 and 3.6.2.

3.6.1 Diameter: Shall be as shown in Table 2.

TABLE 2A - Sizes and Diameter Tolerances, Inch/Pound Units

Form	Nominal Diameter Inch	Tolerance Inch plus	Tolerance Inch minus
Cut Lengths	0.030, 0.035, 0.045, 0.062	0.002	0.002
Cut Lengths	0.094, 0.125	0.003	0.003
Spools	0.007, 0.010, 0.015, 0.020	0.0005	0.0005
Spools	0.030, 0.035, 0.045	0.001	0.002
Spools	0.062, 0.094	0.002	0.002

TABLE 2B - Sizes and Diameter Tolerances, SI Units

Form	Nominal Diameter Millimeters	Tolerance Millimeters plus	Tolerance Millimeters minus
Cut Lengths	0.76, 0.89, 1.14, 1.57	0.05	0.05
Cut Lengths	2.39, 3.18	0.08	0.08
Spools	0.18, 0.25, 0.38, 0.51	0.013	0.013
Spools	0.76, 0.89, 1.14	0.025	0.05
Spools	1.57, 2.39	0.05	0.05

3.6.2 Length: Cut lengths shall be furnished in 18, 27, or 36 inch (457, 686, or 914 mm) lengths as ordered, and shall not vary more than +0, -0.5 inch (-13 mm) from the length ordered.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of wire shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to specified requirements.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Composition (3.1), sizes and tolerances (3.6), and alloy verification (5.2) are acceptance tests and shall be performed on each heat or lot as applicable.