

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 5784

Issued 6-15-52

Revised

STEEL WIRE, CORROSION AND HEAT RESISTANT 29Cr - 9Ni

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily for use as bare wire filler metal.
3. COMPOSITION:

		Check Analysis	
		Under Min	or Over Max
Carbon	0.08 - 0.15	0.01	0.01
Manganese	1.00 - 2.00	0.04	0.04
Silicon	0.75 max	-	0.05
Phosphorus	0.040 max	-	0.005
Sulfur	0.030 max	-	0.005
Chromium	27.00 - 31.00	0.20	0.20
Nickel	8.50 - 10.50	0.15	0.15
Molybdenum	0.50 max	-	0.03
Copper	0.50 max	-	0.03

4. CONDITION: Cold drawn, unless otherwise ordered. Cut lengths or coil sizes and weights shall be as specified by purchaser.
5. TECHNICAL REQUIREMENTS: Melted wire shall flow smoothly and evenly during welding and shall be capable of producing acceptable welds.
6. QUALITY: Wire shall be uniform in quality and condition, clean, sound, smooth, and free from foreign materials and from internal and external defects detrimental to its use for welding purposes.
7. TOLERANCES:
 - 7.1 Unless otherwise specified, straight lengths shall not vary in length more than plus and minus 1/4 in. from the length ordered.
 - 7.2 Unless otherwise specified, diameter of wire shall not vary more than plus and minus 0.002 in. from the size ordered.
8. REPORTS:
 - 8.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report of the results of tests for chemical composition of each heat in the shipment. This report shall include the purchase order number, heat number, material specification number, size, and quantity from each heat.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."